## Permeation breakthrough times and degradation data according to EN ISO 374:2016

## AlphaTec® 02-100

Chemical agent	CAS Number	Breakthrough Time (min)	Protection Index	Degradation (%)	Part
Acetone	67-64-1	> 480	6	11.4	Palm
Acetonitrile	75-05-8	> 480	6	2.2	Palm
Carbon Disulfide	75-15-0	> 480	6	28.2	Palm
Dichloromethane	75-09-2	>480	6	32.4	Palm
Diethylamine	109-89-7	> 480	6	3.2	Palm
Ethyl Acetate	141-78-6	> 480	6	14.4	Palm
Hydrofluoric Acid, 40%	7664-39-3	> 480	6	17	Palm
Methanol	67-56-1	170	4	-7.6	Palm
Nitric Acid, 65%	7697-37-2	> 480	6	4.7	Palm
Tetrahydrofuran	109-99-9	> 480	6	9.8	Palm
Toluene	108-88-3	> 480	6	18.1	Palm

Permeation breakthrough times according to EN ISO 374:2016										
0	1	2	3	4	5	6				
< 10	10-30	30-60	60-120	120-240	240-480	> 480				
Not recommended	Splash protection		Medium protection		High protection					

Data given in the table above are based on results of laboratory tests performed on the palm or cuff area of the glove. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. We wish to highlight that permeation times do not equate to safe wear time. Safe wear time may vary depending on whether the PPE is donned correctly, the surrounding temperature, the chemicals' toxicity, and other factors. Permeation information offered here is limited to the main protective material. Permeation times may vary around seams, zips, visors or any other joins or components of the PPE. It is the responsibility of your organization's Health and Safety professional to undertake a risk assessment before choosing the appropriate PPE for the task at hand. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

## Ansell Healthcare Europe N.V.

Riverside Business Park, Block J Boulevard International 55, 1070 Brussels, Belgium Tel. +32 (0) 2 528 74 00 Fax +32 (0) 2 528 74 01 http://www.ansell.eu E-mail info.europe@ansell.com

